

BITUMASTIC

ELASTOMERIC BITUMINOUS MASTIC

Perfect sealing and waterproofing

Description: Thick, elastomeric, bituminous mastic, based on special polymerized materials, special reinforcing fibers, bitumen and solvents. It is cold-applied.

Usages : It is used for the filling - sealing of joints, cracks, scores formed at the assembly points of concrete, wooden constructions and masonry. It is applied on thin openings of vertical joints, as well. It is also used for the adhesion of bituminous membranes the surface of which is covered by quartz sand, etc. Suitable for application on surfaces made of concrete, lightweight concrete, wood, rock, bricks, plasterboard. It is affected by petroleum products. It should not be applied on surfaces of products made of polystyrene (expanded or extruded), as it contains organic solvents.



Advantages:

- Great adhesiveness.
- It dries quickly.
- It remains flexible at both low and high temperatures (-20° C to +80° C).
- It is water, dilute acids and alkalines resistant.

Packaging: In metal containers of 5 and 20 liters.

Storage: It is stored in roofed spaces (+ 5°C to + 35°C), away from direct sunlight as well as away from heat and fire sources. In a closed container, in the above-mentioned situations, this product is preserved unaltered for an unlimited time.

TECHNICAL FEATURES:

| | |
|--------------------|-----------------------------|
| Form: | Black, thick paste |
| Density: | 0.98-1.02gr/cm ³ |
| Content in solids: | 65-70% |

APPLICATION:

Consumption: 0.10-0.15 lt/meter, for a joint with dimensions of 1cm x 1cm.

Application mode:

- Check surfaces to make sure that they are dry and clean from dirt, oils, rust and rickety ingredients.
- Apply using a spatula or a grease pump for the filling of joints.
- Compress the material appropriately in the joints, ensuring that it is well-fitted. Fill joints up to their surface.
- After 2-3 days, the filling of the joint surface may have lowered. Add bituminous mastic again and re-apply at least 5 cm, on right and left side along the joint.
- In order to protect the bituminous mastic from ultraviolet solar radiation and quick aging, paint the surface that is exposed to the sun, using the bitumen aluminum varnish ALUPASTE.
- Tools should be cleaned immediately after gasoline usage

Εγγυούμαστε για την ποιότητα του προϊόντος, σε ότι αφορά τις τεχνικές προδιαγραφές του, όπως αυτές αποτυπώνονται στη δήλωση επίδοσης (CE) και το τεχνικό φυλλάδιο. Η εγγύηση αυτή αφορά αυστηρά και μόνο το προϊόν που διατίθεται, και σε καμία περίπτωση το τελικό αποτέλεσμα από την εφαρμογή του, το οποίο εξαρτάται σε μεγάλο βαθμό από την εμπειρία και την ποιότητα της εργασίας του εκάστοτε χρήστη, καθώς και τις συνθήκες εφαρμογής. Συνιστάται στον χρήστη να εφαρμόζει το προϊόν δοκιμαστικά, σε μικρή κλίμακα, και αφού βεβαιωθεί για το αποτέλεσμα, τότε να το χρησιμοποιεί στο έργο του. Η έκδοση του παρόντος τεχνικού φυλλαδίου ακυρώνει κάθε προηγούμενη έκδοση αυτού.