

FK 202

High performance, fiber-reinforced, polymer modified adhesive & coating for thermal insulation boards

DESCRIPTION

High performance, fiber-reinforced, polymer modified, cement-based insulation boards adhesive & coating. Ideal for the adhesion of expanded polystyrene (EPS) extruded polystyrene (XPS) as well as mineral wool (MW) boards on surfaces of concrete, render or brick masonry.

Reinforced with suitable fiberglass mesh, can be used for the coating of thermal insulation boards, on external and internal surfaces of buildings.

FIELDS OF APPLICATION

- Use it as adhesive of thermal insulation boards, on surfaces such as concrete, bricks, render, cement blocks, aerated concrete, stone, etc., on exterior and interior surfaces of buildings.
- Used in combination with the decorative finish coat renders MARMOLINE SVR as a system for the external thermal insulation of buildings

- In combination with suitable anchors, which secure the installation, it can be used for coating of thermal insulation boards.
- It is part of a certified External Thermal Insulation Composite System (ETICS).

FEATURES/BENEFITS

- Strong adhesion to the substrate such as concrete, cement, stone, masonry.
- High performance.
- High mechanical strength.
- Fiber-reinforced.
- Excellent workability.
- Easy to handle and apply.
- Low Volatile Organic Compounds.
- User and environmentally friendly.

PRODUCT INFORMATION

Appearance/ color	White powder
Packaging	25kg
Storage conditions	In the original, closed, sealed and indestructible package, protected from direct sunlight and frost and at temperatures from +5°C to + 35°C.
Lifetime	12 months from production date (stored in a closed container in a shady place)

TECHNICAL CHARACTERISTICS

Colour:	White powder
Gradings :	0-0,5 mm
Specific gravity of wet mortar:	1600 Kg/m ³
Compressive strength in 28 days:	22.0 MPa <i>(Average value based on production control laboratory tests)</i> EN 1015-11
Flexural strength in 28 days:	6.0 MPa <i>(Average value based on production control laboratory tests)</i> EN 1015-11
Bond strength with EPS - XPS:	≥ 0.08 MPa - Cohesive failure in the insulation board (ETAG 004)
Bond strength with MW:	≥ 0.01 MPa - Cohesive failure in the insulation board (ETAG 004)
	≥ 0.004 MPa - Cohesive failure in the insulation board, after hygrothermal cycles (ETAG 004)

APPLICATION INFORMATION

Environmental temperature	Temperature from + 5 °C to + 30 °C
Consumption	<ul style="list-style-type: none"> • 4 - 4,5 kg of dry mortar per m², when used as a coating with fiberglass mesh on polystyrene or mineral wool. • 4 - 7 kg of dry mortar per m², depending on the nature of the substrate, when used as insulation boards adhesive
Mixing ratio	About 6 kg (lt) of water /bag of 25 kg.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be stable, dry and free from dust, loosely attached particles and all kinds of dirt. In addition, the surface must be clean, without dust, salts or oil.

APPLICATION

Mix the content of a 25 kg bag, with about 6 lt of water, using a low-rev electric mixer until a homogeneous, lump-free mixture is obtained. Leave the mixture to set for five to ten minutes and stir again.

As an adhesive:

For smooth substrates: The adhesive is evenly spread and combed over the entire surface using a notched trowel at a thickness of 2 - 3 mm.

For uneven substrates: The adhesive is applied in stripes around the edges of the board and in 3 - 4 selected dabs in the center using a notched trowel.

The adhesive must cover the 40% of the boards surface.

Place and press the insulation boards starting from the bottom of the masonry crossways without gaps.

As a reinforced coating:

When used as a fiberglass reinforced coating, apply the mix all over the surface of the insulation board to a thickness of 2 - 3 mm. Place the appropriate MARMOLINE fibreglass mesh to the prepared surface and press with a spatula or trowel until the mesh is fully embedded in the adhesive. The strips of the mesh should overlap by 10 cm approx. Finally, smooth the surface, while simultaneously removing excess mortar.

Suitable anchors should also be used to secure the installation of the insulation boards.

You can use the mixture within 2-4 hours, depending on the environmental conditions (temperature etc.)

CLEANING TOOLS


With plenty of water immediately after use. Hardened and/or cured material can only be removed mechanically.

LEGAL NOTICES

We guarantee the quality of the product, in terms of its technical specifications, as presented in the technical data sheet. This guarantee is strictly only for the available product and in no case the final result from its application, which depends to a large extent on the experience and quality of work of each user, as well as the conditions of application.

It is recommended that the user apply the product on a small scale and after making sure of the result, then use it in his project. Publication of this technical data sheet supersedes any previous version.

MARMOLINE reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

 16 DoP: 206 MAR-CPR
NORDIA S.A. 364 Kifissias Av., 15233 Chalandri, Athens/ Greece
EN 998-1:2016 MARMOLINE FK 202 GENERAL PURPOSE PLASTER
Reaction to fire: Class A2-s1,d0 Water absorption: W _c 2 Water vapour diffusion coef.: μ = 5/20 Adhesion: ≥ 2.2 N/mm ² (FPc) Thermal conductivity/density: (λ _{10,dry}) 0.16 W/mK (tab. mean value; P= 50%) Dangerous substances: see product's SDS Durability (against freeze/thaw, in the intended place of use): NPD