

CHRYSO® Plast GR 120

Set retarding/Water reducing/Plasticizing admixture

DESCRIPTION

CHRYSO®Plast GR 120 is a liquid admixture that retards the initial setting time of the concrete and in combination with a superplasticizer maintains its workability for a long time.

CHRYSO®Plast GR 120 also improves the pumpability of the concrete.

The retardation depends on the dosage of the additive, the climate conditions and the type of cement.

FIELDS OF APPLICATION

- Ready mix concrete
- Concreting at high temperatures
- Transport of concrete over long distances

PACKAGING

- Bulk
- In IBC tanks : 1150 kg (1000lt)
- Drums 200 kg

METHOD OF USE

Dosage: 0.2 – 0.4 kg /100 kg of cement.

The performance of CHRYSO® Plast GR 120 must be determined by trial tests, taking into account the desired rheological and mechanical characteristics of each project. CHRYSO® Plast GR 120 must always be added at the mixing water.

CHRYSO® Plast GR 120 can be used with air-entraining admixtures conformed to EN 934-2 for the production of concretes resistant to freeze-thaw cycles. When air-entraining admixture is used, the two admixtures should be inserted separately.


NORMS & REGULATIONS

CHRYSO®Plast GR 120 is a set retarder, plasticizer complying with the requirements of the European CE marking (EN 934-2, T10).

To obtain the corresponding Declaration of Performance, please contact the sales department.

CHARACTERISTICS

- Nature: Liquid
- Colour: Dark brown
- Specific gravity (20°C): 1.15 ± 0.03 gr/cm³
- pH: 6-8
- Cl⁻ : ≤0.35%
- Na₂O equivalent: ≤5%

 16 0654 DoP No: 412 CHR
NORDIA SA. 364 Kifissias Avenue, 15233 Athens, Greece EN 934-2:2009+A1:2012 CHRYSO PLAST GR 120 Set retarding/water reducing/plasticizing admixture EN 934-2: T10 Chloride ion content: ≤0.15% Alkali content : ≤ 5% Corrosion behaviour: Contains only components according to EN 934-1:2008,Annex A.1 Dangerous substances :see SDS

SAFETY

CHRYSO®Plast GR 120 is a “harmless” product. It is recommended to use the conventional Personal Protective Equipment. For more information, ask the commercial department for the Material Safety Data Sheet.

PRECAUTIONS

- Avoid prolonged exposure to high temperatures
- Protect from frost. Should the product freeze, it will recover its initial consistency. After thawing, an efficient agitation is necessary until the product is entirely homogeneous again.
- Shelf life: 12 months



S-P-11777

NORDIA S.A. : 364 Kifissias Av. & 1 Delfon, 15233 Chalandri
 Tel.: +3022950 22225 e-mail: info@nordia.gr www.marmoline.gr
 Production plant: 1st km Malakasas – Markopoulou Road, 19011 Malakasa, Attica, Greece