under regulation (EU) No 305/2011 and the amendment of Annex III, (EU) No 574/2014

## CHRYSO®Optima 234

0654 15 EN 934-2 0654-CPR-0191

CHRYSO®Optima 234

Unique identification code of the product: It refers to all batches of CHRYSO®Optima 234 produced after the issue

of the present declaration (Batch number: See Product packaging)

High range water reducing / super plasticizing admixtures

EN 934-2: T.3.1/3.2

NORDIA S.A. - MARMOLINE

1st Klm provincial road Markopoulou - Oropou,

Polydendri, Attica, 19014, Greece

System of AVCP:

Harmonized standards: EN 934-2 +A1: 2012

Notified body/ies:

TÜV HELLAS, notified body No 0654, performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment and evaluation of factory

production control, and issued the certificate of constancy of conformity

of the factory production control N° 0654-CPR-0191

Declared performance:

Intended use /es:

Manufacturer:

| Essential characteristics                            | Performance  | Harmonised technical specification |
|--|--|------------------------------------|
| Chloride ion content                                 | ≤0,1%  | EN 934-2+ A1 : 2012                |
| Alkali content                                       | ≤ 2%   | EN 934-2+ A1 : 2012                |
| Corrosion behavior                                   | Contains only components according to EN 934-1:2008, Annex A.1.                        | EN 934-2+ A1 : 2012                |
| Dangerous substances                                 | See MSDS   | EN 934-2+ A1 : 2012                |
| Water Reduction                                      | Test mix ≥12% compared with control mix  | EN 934-2+ A1 : 2012                |
| Compressive strength (at equal consistence)          | At 1 day test mix ≥140% of control mix,<br>At 28 days : Test mix ≥115% of control mix, | EN 934-2+ A1 : 2012                |
| Air content in Fresh concrete (at equal consistence) | Test mix ≤2% by volume above control mix   | EN 934-2+ A1 : 2012                |
| Increase in consistence                              | Increase in flow ≥160mm from initial (350±20 mm)                                       | EN 934-2+ A1 : 2012                |
| Retention of consistence                             | At 30 min: consistence test mix≥ initial consistence of control mix (350±20 mm)        | EN 934-2+ A1 : 2012                |
| Compressive strength (at equal w/c ratio)            | At 28 days: Test mix ≥90% of control mix,  | EN 934-2+ A1 : 2012                |
| Air content in Fresh concrete ( at equal w/c ratio)  | Test mix ≤2% by volume above control mix   | EN 934-2+ A1 : 2012                |
| Dangerous substances                                 | See MSDS   | EN 934-2+A1:2012                   |

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) 305/2011, under the sole responsibility of the manufacturer identified above. Signed for and on behalf of the manufacturer by:



Polydendri, 6/11/2023

QUARRYING AND INDUSTRIAL AND COMMERCIAL CO.S.A. VAT: 50 999211819 364 KIRISSIAS AVENUE HALANDRI 1523 ATHENS OF TEL. 0030 210 68961800

Vivi Dilaveri MSc Civil Engineer NTUA Segment Manager – Concrete admixtures & cement additives