

# ARMOS EPOXY 2-12mm

EN 13888  
RG

## Two component epoxy grout

### DESCRIPTION

Two component epoxy grout, with high mechanical resistance.

### APPLICATION FIELDS

Suitable for 2-12 mm joint widths.

- for surfaces that require high resistance to mechanical loads and chemical effects, as well as waterproofing
- for grouting ceramic and natural stone tiles, indoors and outdoors, on walls and floors, in industrial and commercial premises such as food industries (dairies, canneries, wineries, breweries, slaughterhouses etc.), commercial refrigerators and freezers
- for business environments with high hygiene requirements (butchers, fishmongers, kitchens etc.)
- for industries and chemical laboratories, wastewater storage tanks, public toilets etc.
- for tanks containing chemicals and pools with saltwater or spa water.
- suitable for use on surfaces which contact water intended for human consumption (EN 12873-1 - GCSL p.n.00465/015/000/17.05.2012)

### CHARACTERISTICS/ ADVANTAGES

- It is unaffected by acids, bases, corrosive cleaners, salt water, chlorine, etc.
- It has very good adhesion and is very durable.
- It can be applied very easily, on vertical and horizontal surfaces, and can be cleaned by using hard sponges and clean water.

### PRODUCT INFORMATION

**Packaging:** In plastic packages of 6 kg (5,45 & 0,55 kg) and 3 kg (2,725 & 0,725 kg)

**Storage:** In intact packaging and dry environment, 12 months from the production date.

### TECHNICAL CHARACTERISTICS

- Abrasion resistance:** 165 mm<sup>3</sup> (EN 1208-2)  
**Flexural strength:** 32 N/mm<sup>2</sup> (EN 1208-3)  
**Compressive strength:** 54 N/mm<sup>2</sup> (EN 1208-3)  
**Water absorption:** < 0,1 g (EN 1208-5)  
**Resistance to acids:** Very good  
**Pot life:**  
min 120 min. (23°C and 50% moisture)  
**Application temperature:**  
From +7°C to +35°C  
**Resistance to temperature fluctuation:**  
40°C to 80°C

## APPLICATION INFORMATION

**Consumption :** Indicative consumption:

Tile dimensions cm →	30x60x1	60x60x1	90x90x1	15x90x1
2 mm joint g/m <sup>2</sup> →	185	125	85	290
3 mm joint g/m <sup>2</sup> →	280	185	125	435
4 mm joint g/m <sup>2</sup> →	375	250	165	580
5 mm joint g/m <sup>2</sup> →	470	310	210	730

## APPLICATION INSTRUCTIONS

- The joints must be dry and free from dust, grease and loose particles
- Add component B (hardener) into component A (epoxy resin) and mix well with an electric mixer, for 2-3 minutes at low speed (400 rpm /min), until you get a homogeneous mixture with uniform color
- Make grouting with a rubber spatula, pushing the mixture sideways and diagonally to the joints, until they are filled correctly. At the same time remove the excess material from the surface of the tiles using a hard damp sponge
- Make the final cleaning with a soft sponge (and possibly lukewarm water), moving the sponge diagonally. Thus the joint is smoothed and any grout remaining is removed from the surface of the tiles.
- The use of alcohol facilitates the final cleaning
- It is important to often rinse the sponge, with clean water, during the cleaning process

### ATTENTION:

- Not recommended for use in extreme weather conditions (frost or heatwave). Application temperature +5°C to +35°C

## HEALTH, SAFETY & ENVIROMENTAL PROTECTION

Detailed information and instructions regarding the safe management of the product and in matters of Health & Safety, are provided in the most recent Safety Data Sheet (SDS), copies of which are available on the company's website [www.marmoline.gr](http://www.marmoline.gr) or upon request.

## LEGAL NOTICE

We guarantee the quality of all our products, based on their technical specifications, as described in the Declaration of Performance (CE) and this Technical Data Sheet. Such guarantee refers only to the products that we deliver for use and never to its application or final result, which largely depends on the experience and quality of work of each user and on the application conditions. The user is advised to test the product on a small scale, and if he is satisfied with the result, then to use the product on large scale in his project. All data stated in this Technical Data Sheet are based on laboratory tests. The really measurable data might differentiate due to conditions that are not subject to our control. The recommendations and implementation instructions must be considered by the user as indicative, and always with given that the product has been traded and traded and stored according to its instructions.

As it is not possible to control the parameters/conditions of its application product in practice, no guarantee is provided for the final result of each application. Consequently, no legal liability of the Company can be established based on the information and instruction given in this Technical Data Sheet. The Company reserves the right to modify data listed in this Product Data Sheet, with no previous warning. Users must refer to the latest version of the product Technical Data Sheet.