

## ARMOS EPOXY A+B 2-12 mm

### TWO COMPONENT EPOXY GROUT

**Description :** Two component epoxy grout, with high mechanical resistance. It is classified as RG according to EN 13888.

**Usages:** Suitable for 2-12 mm joint widths

- for surfaces that require high resistance to mechanical loads and chemical effects, as well as waterproofing
- for grouting ceramic and natural stone tiles, indoors and outdoors, on walls and floors, in industrial and commercial premises such as food industries (dairies, canneries, wineries, breweries, slaughterhouses etc.), commercial refrigerators and freezers
- for business environments with high hygiene requirements (butchers, fishmongers, kitchens etc.)
- for industries and chemical laboratories, wastewater storage tanks, public toilets etc.
- for tanks containing chemicals and pools with saltwater or spa water.
- suitable for use on surfaces which contact water intended for human consumption (EN 12873-1 - GCSL p.n.00465/015/000/17.05.2012)



**Advantages:** It is unaffected by acids, bases, corrosive cleaners, salt water, chlorine, etc. • It has very good adhesion and is very durable. • It can be applied very easily, on vertical and horizontal surfaces, and can be cleaned by using hard sponges and clean water.

**Packaging /distribution :** Packages of 3kg & 6kg.

**Storage:** In intact packaging and dry environment, 12 months from the production date. -

**Health and safety :** See product's MSDS

**Specifications:** EN 13888 (RG)

**TECHNICAL DATA:**

<b>Abrasion resistance (EN 1208-2):</b>	165 mm <sup>3</sup>
<b>Flexural strength (EN 1208-3):</b>	32 N/mm <sup>2</sup>
<b>Compressive strength (EN 1208-3):</b>	54 N/mm <sup>2</sup>
<b>Water absorption (EN 1208-5):</b>	< 0.1 gr
<b>Resistance to acids:</b>	Very good
<b>Pot life:</b>	min 120 min. (23°C and 50% moisture)
<b>Application temperature:</b>	from +7°C to + 35°C
<b>Resistance to temperature fluctuation:</b>	-40°C to 80°C

**APPLICATION:**

**Consumption:** Indicative table (g/m<sup>2</sup>):

Tile dimensions (cm)	30 x 60 x 1	60 x 60 x 1	90 x 90 x 1	15 x 90 x 1
Joint 2mm	185	125	85	290
Joint 3mm	280	185	125	435
Joint 4mm	375	250	165	580
Joint 5mm	470	310	210	730

**Application mode:**

- The joints must be dry and free from dust, grease and loose particles
- Add component B (hardener) into component A (epoxy resin) and mix well with an electric mixer, for 2-3 minutes at low speed (400 rpm /min), until you get a homogeneous mixture with uniform color
- Make grouting with a rubber spatula, pushing the mixture sideways and diagonally to the joints, until they are filled correctly. At the same time remove the excess material from the surface of the tiles using a hard damp sponge
- Make the final cleaning with a soft sponge (and possibly lukewarm water), moving the sponge diagonally. Thus the joint is smoothed and any grout remaining is removed from the surface of the tiles.
- The use of alcohol facilitates the final cleaning
- It is important to often rinse the sponge, with clean water, during the cleaning process

ATTENTION:

- Not recommended for use in extreme weather conditions (frost or heatwave).  
Application temperature +5°C to +35°C

The above application guidelines are indicative, for the correct use of the product. For more technical details please contact the company's technical department

*We guarantee the quality of all our products, on the basis of their technical specifications, as described in this technical data sheet. Such guarantee refers only to the products that we deliver for use and never to its application or final result, which largely depend on the experience and quality of work of each user and on the application conditions. The user is advised to test the product on a small scale, and after being satisfied with the result, then to use the product on large scale in his project. This edition of technical data sheet automatically cancels any previous version*